



Independent UV Protection Test

ASTM G154 Cycle # 1
 Lamp Type UVA -340
 .89 Irradance (W/m²) Temp 60° C 8Hrs. UV 4 Hrs. Condensation
 268 Minolta Multi-Gloss Meter

		Start UV Readings	UV Readings after 1779 Hours
Ultra	L	26.78	19.7
	a	-0.02	
	b	0.34	
Competitor A	L	26.79	17.7
	a	-0.1	
	b	-0.52	
Competitor B	L	26.49	2.7
	a	-0.15	
	b	-0.46	
Competitor C	L	26.12	2.2
	a	-0.11	
	b	-0.26	